



VERSATECH PET 3000 RPET EXTRUDED SHEET

Technical Data

Physical Property	Typical Value	Units	ASTM Test Method
Specific Gravity	1.33	g/cm ³	
Melting Point	240 min.	deg C	
Shrinkage	2.0 – 5.0	%	D 955
Tensile Strength @ Yield	7 – 8,800	psi	D 638
Flexural Modulus	300 – 350,000	psi	D 790
Ultimate Elongation	100 – 200	%	D 638
Light Transmission	> 85	%	D 1003
Haze*	< 10	%	D 1003
Clarity	> 97	%	D 1003

VERSATECH PET 3000 RPET complies with all applicable portions of 21CFR177.1630 of the Food and Drug Administration. Information contained herein is considered accurate to the best of our knowledge. It is offered for your consideration and investigation. No warranty is made or implied.

*RPET is derived from diverse feed stocks of POST-USE RECYCLED containers, and as such, there is no representation that the plastic in any order will confirm exactly to the specifications given. HAZE READING ON TYPICAL 0.020 THICK SHEET.

VERSATECH RPET 3000 is also available in white, black and custom colors.

Ex-Tech Value-Added Services

- Sheeting
- Slitting
- Laminating
- Coating
- Corona Treating
- Special Packaging Services
- Warehousing

